

Anschlag-Faserseile nach EN 1492-4



Tragfähigkeit in kg

1-Strang					
direkt					
	Manila Ma	Hanf Ha	Polyamid PA	Polyester PES	Polypropylen PP
			0°		
Ø mm	Lastfaktor 1				
16	250	250	680	520	480
20	400	350	1100	800	750
24	560	500	1500	1200	1100
28	750	700	2100	1500	1400
32	1000	900	2600	2000	1700
36	1300	1200	3200	2500	2200
40	1500	1400	3800	3000	2600
48	2200	2000	5400	4300	3700

Sicherheitsfaktor (SF) 1:7